

# DuFLEX

LIGHTWEIGHT PANEL SOLUTIONS




**Marine. Architectural. Industrial. Transportation.**

The DuFLEX Building System minimizes weight, maximizes mechanical properties, simplifies quotations, and reduces VOC emissions.



# CONTENTS



## The DuFLEX Building System \_\_\_\_\_ 1

### Technical Data \_\_\_\_\_ 2 - 4

Epoxy Matrix _____	2
Skin Mechanical Properties _____	2
Core Mechanical Properties _____	3
Secondary Bonding _____	4
Z Joint _____	4

### Technology vs Cost \_\_\_\_\_ 5

### To Compliment the Duflex System \_\_\_\_ 6 - 9

CNC Routed Temporary Frames _____	6
Strips _____	6
Featherlight _____	7
High Density Inserts _____	8
Full Size Component Packs _____	8
FRP Bonding Angles _____	9
Bonding Angle Performance Data _____	9

### Basic Techniques \_\_\_\_\_ 10 - 11

Joining The Panels _____	10
Processing E-Glass Laminates _____	11

### Markets \_\_\_\_\_ 12

### Safety and Storage \_\_\_\_\_ 13

# The DuFLEX® Building System

## DuFLEX

DuFLEX composite panels were specifically designed to reduce construction time and to optimise structural weight in high performance composite structures. Time consuming laminating, coring and vacuum bagging steps normally required to fabricate high performance composites are avoided, and material waste, labour and tooling costs are greatly reduced.

Standard DuFLEX panels are 1200mm x 2400mm cored with rigid end-grain balsa or structural foam cores, and laminated with a high performance epoxy resin reinforced with multi-axial E-fibreglass or carbon fibre skins. Fibre orientation and ply schedules are based on design or engineering specifications to best meet weight targets, stress and impact loads, and other design parameters.

DuFLEX panels with carbon skins and high performance foam and aramid honeycomb cores can be manufactured for high performance projects requiring superior stiffness or lightweight.

## MANUFACTURE

DuFLEX Panels are manufactured in a controlled environment and under-go strict Quality Inspections at all stages during the manufacturing process to ensure dimensional stability and consistent thickness.

The core and laminates are co-cured in a hot press, a method that consolidates the laminate under pressure increasing the fibre volume and therefore the strength of the finished panel. The E-glass fibre content of DuFLEX laminates is approximately 62% by weight.

The panels are finished with peel ply to protect the laminates from contamination and to reduce the amount of preparation required prior to secondary bonding or laminating.

Highly-respected, international certification body, DNV-GL has audited production facilities and manufacturing processes at ATL and issued Shop Approval KBZ 1095 HH for The Production of Composite Panels.



## FEATURES

- Strength
- Durability and Damage tolerance
- Lightweight
- Dimensionally Stable
- Code Approved Manufacture Available



## SUPPORT

The DuFLEX Building System is backed with comprehensive technical information and an experienced Technical Team. Technical assistance is available to provide guidance on how to utilise the structural advantages of DuFLEX during the construction process.

Engineering Support Services are also available to ensure that projects meet design loadings and regulatory requirements.

- Consultation with designers, architects and structural engineers
- Composite engineering expertise including Finite Element Analysis
- Recommendations for approved fabricators.

# TECHNICAL DATA

## EPOXY MATRIX

By using epoxy rather than polyester resin as the matrix in DuFLEX, a reduction of laminate thickness is achieved while improving damage tolerance. Epoxy exhibits better moisture and fatigue resistance, and has superior strain capabilities which provides DuFLEX laminates with greater impact resistance than polyester / E-glass laminates that are up to 3 times thicker.

Epoxy's excellent adhesion to balsa and foam cores, fibreglass, aramid and carbon fabrics allows the builder the advantage of selectively integrating these

materials into a structure to optimise strength, cost and weight.

Compared to polyester resins, epoxies have greater strength, less shrinkage, better moisture and fatigue resistance, and there is no chance of osmotic blistering occurring in an epoxy matrix.

Tensile Modulus	3.650 MPa	(0.53+6psi)
Tensile Strength	83.3 MPa	(12,800psi)
Tensile Elongation	9.8%	
Compressive Strength (Yield)	98 MPa	(14,210psi)
Compressive Strength (ultimate)	130 MPa	(18,850psi)
Izod Impact	0.598 ft.lb/in notch	



## SKIN MECHANICAL PROPERTIES

Standard DuFLEX skin laminates are constructed using stitched biaxial E-glass, the material provides excellent properties in both warp and fill directions, surpassing American Bureau of Shipping (ABS) requirement for balanced laminates.

Compared to the ABS minimum tensile strength for basic laminate, DuFLEX skin laminates show far superior performance.



ABS Basic Laminate	Tensile Strength	Tensile Modulus
Warp (0°)	124.1 MPa (18,000 psi)	6,890 MPa (1.0E + 6 psi)
Fill (90°)	99.28 MPa (14,400 psi)	6,890 MPa (1.0E + 6 psi)

DuFLEX Skin Laminate	Tensile Strength ASTM D3039	Tensile Modulus ASTM D3039
Biaxial-Warp (0°)	371.9 MPa (53,900 psi)	21.27 GPa (3.08E + 6 psi)
Biaxial-Fill (0°)	327.6 MPa (47,500 psi)	18.22 GPa (2.64E + 6 psi)

Laminate Thickness	0.53mm per 600gsm (0.021" per 18oz)	
Fibre Fraction	62-64% weight fraction	
Poisson's ratio	0.10	

Compressive values have been extrapolated from sandwich flexural tests (ASTM C-273) conducted at the University of Southampton, UK in which skin bending was negligible.

DuFLEX Skin Laminate	Compressive Strength	Compressive Modulus
Biaxial-Warp (0°)	293.8 MPa (42,600 psi)	21.27 GPa (3.08E + 6 psi)
Biaxial-Fill (90°)	255.5 MPa (37,000 psi)	18.22 GPa (2.64E + 6 psi)

DuFLEX Skin Laminate	Increase over ABS
Biaxial-Warp (0°) Tensile Strength	+300%
Biaxial-Fill (90°) Tensile Strength	+330%

# TECHNICAL DATA

## CORE MECHANICAL PROPERTIES

RIGID END-GRAIN PROBALSA®		
Nominal Density	ASTM C-271	155 kg/m <sup>3</sup>
Tensile Strength	ASTM C-297	13.5 MPa
Compressive Strength	ASTM C-365	12.7 MPa
Compressive Modulus	ASTM C-365	4,100 MPa
Shear Strength	ASTM C-273	3.0 MPa
Shear Modulus	ASTM C-273	166 MPa

PVC FOAM DIVINYCELL® H80		
Nominal Density	ISO 845	80 kg/m <sup>3</sup>
Tensile Strength	ASTM D-1623	2.5 MPa
Tensile Modulus	ASTM D-1623	95.0 MPa
Compressive Strength	ASTM D-1621	1.4 MPa
Compressive Modulus	ASTM D-1621-B-73	90.0 MPa
Shear Strength	ASTM C-273	1.15 MPa
Shear Modulus	ASTM C-273	27.0 MPa
Shear Strain	ASTM C-273	30%

® Registered trademarks of The Diab Group

## STANDARD PANELS

### DuFLEX Balsa

Order Code	Core Thickness	Nominal Weight kg/m <sup>2</sup>
------------	----------------	----------------------------------

→ 1 x 600g Biaxial E-glass either side of core\*

DP1010C6	10mm	4.2
DP1013C6	13mm	4.6
DP1016C6	16mm	5.1
DP1019C6	19mm	5.6
DP1025C6	25mm	6.4

→ 2 x 600g Biaxial E-glass either side of core

DP2010C6	10mm	6.0
DP2013C6	13mm	6.4
DP2016C6	16mm	6.9
DP2019C6	19mm	7.4
DP2025C6	25mm	8.3

### DuFLEX Foam

Order Code	Core Thickness	Nominal Weight kg/m <sup>2</sup>
------------	----------------	----------------------------------

→ 1 x 600g Biaxial E-glass either side of core\*

DD1010C6	10mm	3.1
DD1012C6	12mm	3.3
DD1015C6	15mm	3.5
DD1020C6	20mm	3.8
DD1025C6	25mm	4.2

→ 2 x 600g Biaxial E-glass either side of core

DD2010C6	10mm	4.9
DD2012C6	12mm	5.0
DD2015C6	15mm	5.2
DD2020C6	20mm	5.7
DD2025C6	25mm	6.2

\* Alternative laminates and cores are available on request.


ATL Composites Pty Ltd reserve the right to alter specifications without prior notice. Weight may differ slightly (up or down) due to variations in core density.

# TECHNICAL DATA

## SECONDARY BONDING

The issue of secondary bonding between polyester and epoxy substrates has been an area of concern for some time. Comparative in-house tests have abounded, but without quantitative results they can only demonstrate modes of failure and give a 'feel' for the force required at break. ISO 527 was modified to accommodate a tensile double lap joint. Four types of specimen were tested to show that polyester tabbing has the same strength when bonding polyester or epoxy substrates.

(See table below for specifications).



### SECONDARY BONDING LAP JOINT TEST RESULTS

	Failure Load	Apparent Shear Strength	Failure Mode*
A	42.45 kN (9,540 lbf)	5.66 MPa (820 psi)	Interlaminar Shear**
B	48.47 kN (10,900 lbf)	6.46 MPa (937 psi)	Interlaminar Shear
C	46.50 kN (10,450 lbf)	6.20 MPa (899 psi)	Interlaminar Shear
D	47.08 kN (10,580 lbf)	6.28 MPa (911 psi)	Interlaminar Shear

\* International Failure occurred with the CSM layer of tabbing laminates.

\*\* One specimen showed adhesive failure between the tabbing and substrate.

A - Polyester peel plied substrate, polyester tabbing

B - Polyester sanded substrate (80 grit), polyester tabbing

C - Epoxy peel plied substrate, polyester tabbing

D - Epoxy sanded substrate (80 grit), polyester tabbing


This data is provided as an aid to materials selection only. No express or implied warranty is made regarding the accuracy of the information contained herein.

## Z-JOINT

To offset their individual size, DuFLEX panels can be supplied with both long edges pre-machined to facilitate joining. This Z-Joint is structurally effective and achieves a smooth and fair surface profile. The Z-Joint must be bonded with a high density epoxy adhesive mixture.

Particularly in strength critical applications the Z-Joint must be given adequate consideration. It can be considered analogous to a weld in aluminum, as a strength reduction exists. The Z-Joint must be bonded with a high density epoxy adhesive mixture.

Testing indicated no reduction in modulus, resulting in continuity of panel stiffness and fairness during formation. For example in the majority of marine applications stiffness is critical and therefore a strength reduction in the laminate due to the joints presence is normally of little consequence. A weft unidirectional tape can be used in situations where strength continuity is desired.



DuFLEX Skin Laminate	Tensile Strength ASTM D3039	Strength Reduction
Biaxial-Warp (0°)	298.6 MPa (43,310 psi)	19.8%
Biaxial-Fill (90°)	262.9 MPa (38,130 psi)	19.8%
Unidirectional-Warp (0°)	488.6 MPa (70,870 psi)	16.6%
Unidirectional-Fill (90°)	23.0 MPa (3,330 psi)	0.00%

# TECHNOLOGY VS COST

## KITS

Whether in computers, airplanes or boats, high tech is often associated with high cost. Time is valuable and there is no doubt that DuFLEX, especially in kit form, speeds up construction.

Computer-aided design and manufacture (CAD/CAM) processes combined with computer numeric control (CNC) equipment allows the production of pre-fabricated DuFLEX Kits. Parts to be formed into curved surfaces can be translated by design software into the correct flat panel shapes, and this electronic information is supplied to ATL Composites Engineering Department where all parts required for the project are nested together within the panels to reduce wastage.

Once the panels are manufactured, the CAD information is used by a CNC router to machine the programmed shapes into the panels, and Z-Joints are machined on the edges, either long or short, depending on nesting orientation, to facilitate joining of the kit.


The panels are sequentially numbered to indicate the correct joining sequence, and a nesting diagram, showing part numbers and descriptions is supplied for easy identification.



Each pre-cut part is left attached to the panel by small tabs to ensure the kit arrives with all components securely in place. The tabs are easily cut away, when the panels have been joined.

## OPTIMISED KIT TECHNOLOGY

- Minimises material waste, labour & tooling costs
- Maximises mechanical properties
- Tightens design allowables
- Improves product quality
- Simplifies quotations
- Reduces VOC emissions



MOTOR YACHT NESTING EXAMPLE

# TO COMPLIMENT THE DUFLEX SYSTEM

## CNC-ROUTED TEMPORARY FRAMES



CNC-Routed plywood or MDF (medium density fibre-board) temporary frames can also be supplied to provide the builder with accurate sections, cut exactly to drawing specifications. Frames can be cut to shape and flat packed, and shipped to the fabricator. Parts are labeled and stacked sequentially on the pallet, and can include details like station numbers, reference lines, and notches, and an assembly booklet is supplied.

Frames can be assembled without the need for power tools or heavy equipment, and parts lock securely and accurately to optimise assembly time, reducing waste and improving job site safety.

## STRIPS

Compound surfaces are common in marine applications, for example sail boat hulls and the flared topsides in sport fishing boats. These surfaces can be made by bending and edge gluing DuFLEX Strips around temporary frames, as with traditional strip planking.

DuFLEX strips are pre-laminated with unidirectional reinforcements, in a 1200mm x 2400mm sheet with Z-Joints on both short ends.

The unidirectional fibre allows the planks to conform readily to highly convex or concave contours and can provide up to 50% of the total laminate. The ability to place a large percentage of the reinforcement mass during planking has obvious time-saving benefits.

The stiffness of the DuFLEX Strips allows them to bend fairly over half the number of the frames required by other strip systems, and increases the stability when turning a boat hull.

The laminating required to complete the structure can be applied after the part shape has been stripped.



Laminate Type	Tensile Strength ASTM D3039	Tensile Modulus ASTM D3039
Unidirectional @ (0°)	585.6 MPa (84,900 psi)	34.73 GPa (5.04E + 6 psi)
Unidirectional @ (90°)	23.00 MPa (3,330 psi)	8.295 GPa (1.20E + 6 psi)
Laminate Thickness	0.88mm per 800gsm (0.035" per 23.5oz)	
Fibre Fraction	62-64% weight fraction	
Poisson's Ratio	0.26	



# TO COMPLIMENT THE DUFLEX SYSTEM

## FEATHERLIGHT

Specifically designed for non-structural applications Featherlight™ panels have been developed to optimise weight and dimensional stability.

Featherlight Panels are available with a choice of low-density PVC foam or select grade balsa cores to provide superior levels of stiffness, and thermal, or acoustical, insulating properties.

The panels are finished with either hardwood veneers or peel-plyed, reinforced epoxy laminates. The timber-faced panels are supplied with a sanded, calibrated surface that is ready for decorative veneer application, painting or secondary bonding with decorative laminate.

Custom thicknesses can be manufactured, on request and a selection of core types and densities are available to provide a range of weight, stiffness and cost options. From economical lower density foam cores through to the more expensive aramid honeycomb used in weight critical, high performance projects, all Featherlight panels provide significant weight savings over traditional plywood panelling.

Featherlight is ideally suited for construction of interiors for luxury, and high performance, motor and sailing yachts in Marine applications. Featherlight can also be used for walls, roof panels, interior partitions in Architectural, Rail and Transportation applications, and other structures requiring thermal and acoustical insulating properties.



PVC FOAM DIVINYCELL® H60		
Nominal Density	ISO 845	60 kg/m <sup>3</sup>
Tensile Strength	ASTM D-1623	1.8 MPa
Tensile Modulus	ASTM D-1623	75 MPa
Compressive Strength	ASTM D-1621	0.9 MPa
Compressive Modulus	ASTM D-1621-B-73	70 MPa
Shear Strength	ASTM C-273	0.76 MPa
Shear Modulus	ASTM C-273	20 MPa
Shear Strain	ASTM C-273	20%

® Registered trademark of The Diab Group

## STANDARD PANELS

FEATHERLIGHT FF		
Order Code	Core Thickness	Nominal Weight kg/m <sup>2</sup>
→ 1 x 600g Biaxial E-glass either side of core*		
FF1009C6	9 mm	3.1
FF1012C6	12 mm	3.2
FF1015C6	15 mm	3.4
FF1019C6	19 mm	3.7

Tolerance for FF1015C6 is +/- 0.2mm. Panel size is 1200mm x 2400mm - other dimensions, laminates and closer tolerance upon request.



## TO COMPLIMENT THE DUFLEX SYSTEM

### HIGH DENSITY INSERTS

DuFLEX and Featherlight panels can also incorporate High Density Inserts using materials such as PVC foam, PET foam, high density Coosa polyurethane foam and solid FRP.

By including High Density Inserts it will allow for effective surface screw fixing, tapping and through-bolting without the risk of localised pull-out, buckling or compression failures. Inserts can also be used locally for perimeter edging in order to offer a more robust and impact resistant panel edge, often eliminating the need for de-coring.

Having Inserts included in the panel manufacture, and not having to fit on the job, offers fabricators significant savings in labor and wastage.

\*Options are also available for specialised inserts including aluminium flat bar, PVC conduit and FRP pultrusions.


All DuFLEX and Featherlight Panels are compatible with a variety of resins for post lamination and bonding including Polyester, Vinyl Ester, Epoxy and Polyurethane.



### FULL SIZE COMPONENT PACKS

Tight build schedules are placing additional pressure on composite manufacturers worldwide. ATL Composites can now supply Full Size Component Packs to reduce build times and reduce wastage.

DuFLEX and Featherlight panels are manufactured and routed as per our standard processing, then ATL trained staff join the panels, release and trim the parts at our facility, to supply Full Sized Parts including Bulkheads, Floors, Soles, and Interior Fit-outs directly to our customers. The Full Sized Components are securely packed for freighting and arrive ready to install, simply tape into place.



# TO COMPLIMENT THE DUFLEX SYSTEM

## FRP BONDING ANGLES



Composite 90° Bonding Angles have been designed to provide a quick and effective means for making right angle joints between DuFLEX and Featherlight Panels. These pre-cured angles can be bonded in place with an epoxy paste adhesive, speeding up assembly and reducing wet lay-up. They are also ideal for inaccessible areas where wet-fibreglass taping would be difficult.

All FRP Bonding Angles are supplied in 2400mm lengths and consist of layers of multi-axial E-glass in a high performance epoxy matrix, with the fiber direction tailored for optimum load-carrying capability and stiffness. The bonding angles are manufactured with peel ply to provide a textured surface to aid in secondary bonding. The peel ply is removed by ATL prior to supply.

The automated combination of resin matrix, fibre content and orientation assures optimum mechanical properties while the use of an epoxy adhesive enhances the bond strength.

Composite Bonding Angles are lighter than equivalent aluminum, steel or timber sections, with superior resistance to corrosion and fatigue. No wet-lay-up is required, they are simply installed with appropriate surface preparation.

### FEATURES

- Lighter and More Consistent than Wet Lay-Up
- Faster to Install, especially Over-Head
- Extremely High Strength to Weight Ratio
- Can be Kerfed and Curved for Partition Bases

## BONDING ANGLE PERFORMANCE DATA

Queensland University of Technology (QUT) test report CET 4149/3 - Tensile tests to fibreglass connections - fins.

→ SAMPLE DATA: Specimen 1 - polyester bonded

Specimen 2 - epoxy bonded

Test Equipment: Grade A Tinius Olsen Universal Testing Machine, loading rate = 5mm/min

Specimen Thickness	Failure Load (kN)	Failure Mode	Apparent Shear Strength (MPa)	Nominal Area Resisting Shear (mm²)
21	77.6 part shear through polyester bond	Adhesive Failure	1.60	48,400
14	68.5kN shear through epoxy bond	Adhesive Failure	2.25	30,400

In both circumstances, failure of the joints was through the adhesive rather than the Bonding Angle.

## STANDARD ANGLES

FRP BONDING ANGLES			
Order Code	Description	Leg Length	Nominal Weight
ANT3042	90° Bonding Angle	42 mm	0.30 kg/m
ANT5084	90° Bonding Angle	84 mm	1.00 kg/m


# BASIC TECHNIQUES

## JOINING THE PANELS

### Z-PRESS

To streamline the joining process, the proprietary Z-Press applies heat and pressure to cure the epoxy adhesive on the Z-Joints. Joins are fully cured in 7 to 20 minutes, depending on the ambient temperature, type of hardener, core type and thickness of the panel. Checking the “squeeze-out” on the joint until it has become rubbery, will indicate when you can proceed with the next join.

Drums, or a purpose-built receiving stand, should be set up to support the full sized panel being joined. Once joined, the tabs can be cut to remove the full size parts of the DuFLEX kit. Large parts, for example a topside panel, of a boat hull may extend through two or more panels, so the panels should be joined before the tabs are cut.



### APPLYING ADHESIVE TO THE Z-JOINT

Prior to applying adhesive to the Z-Joint, carefully remove approximately 25mm of peelply from the outside edge of the male scarf, taking care not to damage the laminate. Scarfs should be brushed with a clean brush to remove dust and any contamination that would inhibit adhesion.

It is important to apply enough high-density adhesive to cover both Z-joints and exposed core, and to allow adequate squeeze out when the joints are pushed together.

The panels should be pushed together by sliding them back and forth to make a tight join of no more than 1mm, prior to applying pressure with the Z-Press or manual joining strips.




### MANUAL JOINING

#### STEP 1


Take two strips of 100mm wide, 19mm MDF (fibreboard) the length of the long side of the composite panel (2400mm).

Cover one side of each strip with plastic tape as shown. Drill pairs of 3mm (approx.) screw holes, 30mm each side of centre, through one strip at 100mm centres.




#### STEP 2

Apply a high-density epoxy adhesive to both Z-Joints, making sure there is adequate adhesive to cover all core and scarf joint areas, and push joints together with a maximum gap of 1mm.




#### STEP 3

Lay the strip with no holes, plastic side up, underneath the glue joint; lay the holed strip, plastic side down, on top of the glue joint.



#### STEP 4

Screw through the holed top strip into the bottom strip, ensuring faces are squeezed together firmly. Leave to cure overnight.



# BASIC TECHNIQUES

## PROCESSING E-GLASS LAMINATES

Diamond-coated fiberglass tooling is recommended for cutting for best tool life, for example, a jigsaw with a Makita No.10S Type 150 blade to cut out parts. The best edge finish is achieved with circular saws running aluminum cutting blades, however blade life is greatly reduced.

### CURVATURES AND RADII

Curved surfaces are achieved without effort by simply kerf-cutting the inside skin. The need for elaborate moulds is not necessary, simple jigs can be used to form a variety of corners and curves.


### METHOD A - Construction of large radii curves

Curves of 60 to 90 degrees are achievable with no loss of structural integrity.

#### STEP 1

A series of narrow parallel slots (kerfs) are cut into the sandwich panel along the inside of the proposed curve, through the facing skin and core to the rear face of the outside skin. The saw cuts should never break through the outer facing skin, which serves as a hinge.

Initially determine the desired internal angle, and outer corner radius. Following the calculations below, will provide the required details on number of slots, and their spacing, to achieve the required curve.



$\alpha$ - Internal angle	$t$ - Panel thickness
0.52 (150°) 1.57 (90°)	$c$ - Saw cut centres
1.05 (120°) 2.62 (30°)	$R$ - Corner radius
$s$ - Saw cut width	$n$ - Number of slots

$$n = \frac{t \cdot \alpha}{s}$$


Example:  $\frac{16\text{mm} \times 1.57}{2} = 12$

$$c = \frac{R \cdot \alpha - s}{n - 1}$$

Example:  $\frac{50\text{mm} \times 1.57 - 2.2}{12} = 5\text{mm}$

#### STEP 2

Fill the saw cuts with a thickened epoxy mixture and bend to the final shape and allow to cure. The shape should be held in position, while the epoxy cures, with clamps or jigs.



#### STEP 3


An additional layer of fibreglass cloth is applied to the inside of the curve with an epoxy laminating system, covering all the slots and overlapping the end slots by 30mm to 40mm.

### METHOD B - Construction of small radii curves

#### STEP 1

A strip of the panel is removed by cutting through the facing skin and core to the rear face of the outside skin. The slot width is calculated by:


$$\text{Slot width} = a \cdot t$$



#### STEP 2

The cut should be filled with a mixture of WEST SYSTEM 105 resin with 206 Slow hardener, modified with 411 Microsphere Blend. This combination will produce a strong, waterproof bond that will hold the curve when cured.


Apply enough modified epoxy to fill the internal angle left by the removed skin and core material. Allow to cure. The shape should be held in position, while the epoxy cures, with clamps or jigs.



#### STEP 3

Fill the internal angle, with a 20mm radius of modified epoxy and allow to cure.

Apply an additional layer of fibreglass cloth to the inside of the angle, overlapping the fillet by 25mm on each side.



# MARKETS

## MARINE



DuFLEX Composite Panels have become an industry standard for composite boat construction and can be engineered and manufactured to meet the rules of all major Marine Authorities including Lloyd's Register of Shipping, American Bureau of Shipping, CE, DNV-GL and Australian Standard.

- Recreational /pleasure craft
- Cruising and racing yachts
- Mega-yachts
- High speed ferries
- Water taxis
- Patrol craft

## ARCHITECTURAL



With DuFLEX and Featherlight panels, complex forms can be created, broadening design freedom and offering rapid processing and construction which helps to lower costs significantly.

They can provide new construction solutions, alone or in conjunction with traditional materials.

- Building facades
- Structural cladding
- Doors, gates & window frames
- Long span roofing
- Acoustic insulation
- Prefabricated housing
- Composite decks & bridges

## INDUSTRIAL



DuFLEX Composite Panels offer excellent durability, acoustic insulation properties and high chemical resistance, making them an ideal alternative to steel, iron and concrete for industrial applications, reducing maintenance and life cycle costs.

- Holding Tanks and Lids
- Staging, Walkways and Scaffolding
- Form Work
- Audio Visual Equipment Containers

## TRANSPORTATION



Composite materials provide strength, lower vehicle weight and improved energy efficiency in transportation applications.

DuFLEX and Featherlight panels allow for design flexibility and deliver the optimum combination of weight, performance, reduction in operating costs and safety.

### Road Transportation

- Truck beds, bodies and side walls
- Bus floors


### Rail Transportation

- Flooring
- Roof / ceiling construction
- Cabinetry and interiors
- Doors

# SAFETY AND STORAGE

## SAFETY

Avoid inhalation and eye contact with machining dust. Wear protective equipment such as hearing protection and safety glasses during cutting operations, and gloves to avoid cuts. Use guards as per machinery manufacturers instructions.



## STORAGE

DuFLEX and Featherlight panels should be stored flat, out of direct sunlight, and kept dry and clean. Panels supplied with fibreglass skins have peel-ply on the surface, which should be left in place as long as possible, to protect them from surface contamination.



[www.duflex.com.au](http://www.duflex.com.au)



**Company Name** ATL Composites Pty Ltd

**ABN** 26 002 517 777

**Established** 1977

**Location** 12-14 Production Ave. Molendinar QLD, Australia 4214

**Phone** +61 7 5563 1222

**Fax** +61 7 5563 1585

**Email** [info@atlcomposites.com](mailto:info@atlcomposites.com)



**Manufactured in Germany for the European Market by**

**Company Name** vdL Composites GmbH

**Location** An der Windmühle 2, 46483 Wesel, Germany

**Phone** +49 (0)281 33830 0

**Fax** +49 (0)281 33830 30

**Email** [info@vdlcomposites.de](mailto:info@vdlcomposites.de)

